




TECHNICAL CHARACTERISTICS
ACCORDING TO ANSI 1371 (Especificaciones técnicas)

| TECHNICAL CHARACTERISTICS | TEST METHOD ASTM | REQUIRED VALUE ANSI 1371 | FACTORY VALUE I-D/HD |
|---------------------------|-------------------------|---|--|
| WATER ABSORPTION | ASTM C373 | 0.5% (fully vitrified) | ≤ 0.06 |
| BREAKING MODULUS | ASTM C648 | 2250 Pounds 2115 kg 21110 N | COMPLIANT |
| MOHS HARDNESS | ASTM C501 | ≥ 400 | TEST METHOD EN 101 POLISHED MOHS 5 NATURAL MOHS 6 |
| ABRASION RESISTANCE | ASTM C1243 | NOT REQUIRED | 1.51 MILLION ISO 10545.7 PER Y |
| THERMAL SHOCK RESISTANCE | ASTM C484 | REQUIRED | RESISTANT |
| CHEMICAL RESISTANCE | ASTM C650 | NOT REQUIRED | RESISTANT |
| FROST RESISTANCE | ASTM C1026 | NOT REQUIRED | RESISTANT |
| BOND STRENGTH | ASTM C482 | 250 PSI 20.5 Kg/cm ² 20.34 N/mm ² | COMPLIANT |
| STAIN RESISTANCE | CTI 81-7 | NOT REQUIRED | RESISTANT |
| THICKNESS | ASTM C485 Worpage | < 1/8" (0.125") ≤ 0.3175" (8.08 mm) | COMPLIANT |
| | ASTM C499 Dimensions | < 3/32" (0.9375 mm) (Maximum) ± 1/32" (0.3125 mm) (Tolerance) between tile and metal retile | COMPLIANT |
| | ASTM C199 Tickness | ± 0.002 inch 0.05 mm (with tolerance for warpage not a issue) | COMPLIANT |
| | ASTM C502 Wedging | ± 0.015" | COMPLIANT |
| COF | ASTM C1028-96 | ≥ 0.40 | POLISHED ^{max} 0.68 ^{min} 0.41 |
| | | | NATURAL ^{max} 0.80 ^{min} 0.43 |



CALACATTA

Porcelain



CALACATTA

GROUT JOINT REQUIRED FOR RECTIFIED EDGE TILE
1/2 BROKEN JOINT NOT RECOMMENDED



12,6"x25,2" RECTIFIED EDGE
NATURAL




19"x19" RECTIFIED EDGE
NATURAL



3,2"x12,6" BULLNOSE
NATURAL



12,6"x12,6" SHEET
1"x1" NATURAL MOSAIC



12,6"x12,6" SHEET
BRICK DECO MOSAIC
SEMI-POLISHED



0,6"x12,6" METAL PENCIL

0,6"x0,6" METAL PENCIL
CORNER




12,6"x25,2" RECTIFIED EDGE
SEMI-POLISHED



19"x19" RECTIFIED EDGE
SEMI-POLISHED



3,2"x12,6" BULLNOSE
SEMI-POLISHED



12,6"x12,6" SHEET
PINWHEEL DECO MOSAIC
SEMI-POLISHED



12,6"x12,6" SHEET
1"x4" SEMI-POLISHED

