




	TECHNICAL CHARACTERISTICS	REFERENCE STANDARD	REQUIRED VALUE	AVG. VALUE
	DIMENSIONS	ISO 10545-2	Compliant	Compliant
	WATER ABSORPTION	ISO 10545-3	≤0,5 %	<0,1%
	MODULUS OF RUPTURE	ISO 10545-4	MODULUS OF RUPTURE R ≥ 35 N/mm <sup>2</sup> BREAKING STRENGTH S ≥ 1300 N	R>50 N/mm <sup>2</sup> S>2500 N
	SCRATCH RESISTANCE	ISO 10545-7	0 - V	IV
	LINEAR THERMAL EXPANSION	ISO 10545-8	≤ 9x10 <sup>-5</sup> °C <sup>-1</sup>	6x10 <sup>-5</sup> °C <sup>-1</sup>
	THERMAL SHOCK RESISTANCE	ISO 10545-9	Resistant	Resistant
	FROST RESISTANCE	ISO 10545-12	Resistant	Resistant
	ACID AND ALKALI RESISTANCE	ISO 10545-13	CLASS GB MIN.	Low concentr. GLA High concentr. GHA
	CHEMICAL RESISTANCE	ISO 10545-13	CLASS GB MIN.	GA
	STAIN RESISTANCE	ISO 10545-14	CLASS 3 MIN.	5

FRICION COEFFICIENT (SLIPPERINESS)	BCR - Italia DM del 14-06-89			ASTM - USA ASTM C1028		DIN - Germania DIN 51130
	Dry rubber 0,62	Wet rubber 0,51	Dry leather 0,62	Dry neolythe 0,69	Wet neolythe 0,62	R9 ZH 1/571
THE PRODUCTS HAVING AN ABSORPTION < 0,5% ARE CLASSIFIED ACCORDING TO THE UNI CEN STANDARDS "FULLY VITRIFIED TILES" AND ACCORDING TO THE ASTM STANDARDS "IMPERVIOUS TILES"						



**E-STONE**  
FULL BODY PORCELAIN

E-STONE BLACK


E-STONE GREY

E-STONE WHITE




**E-STONE BLACK**

12"x24"




Bullnose 3"x12"

Mosaic 1.25"x4" (12"x12" Sheet)




**E-STONE GREY**

12"x24"



Bullnose 3"x12"

Mosaic 1.25"x4" (12"x12" Sheet)




**E-STONE WHITE**

12"x24"



Bullnose 3"x12"

Mosaic 1.25"x4" (12"x12" Sheet)



Mosaic mix 1.5" x 1.5"  
(12" x 12" sheet)



Universal Metal Pencil 0,6"x12"



Universal Metal Corner 0,6"x0,6"