


Hickory Specs

HICKORY PEI RATING:

FOG	IV	HONEY	IV	CHERRY	IV
-----	----	-------	----	--------	----

SHADE INDEX: HICKORY HAS A SHADE VARIATION OF V3

V1 = UNIFORM APPEARANCE
V2 = LOW VARIATION
V3 = MEDIUM VARIATION
V4 = HIGH / RANDOM



MOHS RATING:

FOG	7	HONEY	7	CHERRY	7
-----	---	-------	---	--------	---

PRE & POST CONSUMER RECYCLED CONTENT

	FOG	HONEY	CHERRY
PRE-CONSUMER	40%	40%	40%
POST-CONSUMER	0%	0%	0%
MANUFACTURED	ITALY	ITALY	ITALY

SIZE & TRIM / MOSAIC DATA

NOMINAL SIZE	ACTUAL SIZE	METRIC (CM)	THICKNESS
6"X36"	5 3/4" X 35 1/4"	14,5 X 89,4	6/16"

TRIM / MOSAIC

3,2"X18" BULLNOSE	3 3/8" X 17 3/4"	8 X 45	6/16"
-------------------	------------------	--------	-------

	TECHNICAL CHARACTERISTICS	REFERENCE STANDARD	REQUIRED VALUE	AVG. VALUE		
	DIMENSIONS	ISO 10545-2	Compliant	Compliant		
	WATER ABSORPTION	ISO 10545-3	≤0,5 %	<0,1%		
	MODULUS OF RUPTURE	ISO 10545-4	MODULUS OF RUPTURE R ≥ 35 N/mm ² BREAKING STRENGTH S ≥ 1300 N	R>50 N/mm ² S>2500 N		
	SCRATCH RESISTANCE	ISO 10545-7	0 - V	IV		
	LINEAR THERMAL EXPANSION	ISO 10545-8	≤ 9x10 ⁻⁵ °C ⁻¹	6x10 ⁻⁵ °C ⁻¹		
	THERMAL SHOCK RESISTANCE	ISO 10545-9	Resistant	Resistant		
	FROST RESISTANCE	ISO 10545-12	Resistant	Resistant		
	ACID AND ALKALI RESISTANCE	ISO 10545-13	CLASS GB MIN.	Low concentration GLA High concentration GHA		
	CHEMICAL RESISTANCE	ISO 10545-13	CLASS GB MIN.	GA		
	STAIN RESISTANCE	ISO 10545-14	CLASS 3 MIN.	5		
	FRICTION COEFFICIENT (SLIPPERINESS)	BCR - Italia DM del 14-06-89			ASTM - USA ASTM C1028	DIN - Germania DIN 51130
		Dry rubber 0,62	Wet rubber 0,51	Dry leather 0,62	Dry neolythe 0,69	Wet neolythe 0,62

THE PRODUCTS HAVING AN ABSORPTION < 0,5% ARE CLASSIFIED ACCORDING TO THE UNI CEN STANDARDS "FULLY VITRIFIED TILES" AND ACCORDING TO THE ASTM STANDARDS "IMPERVIOUS TILES"



PRE & POST CONSUMER RECYCLED CONTENT

	FOG	HONEY	CHERRY
PRE-CONSUMER	40%	40%	40%
POST-CONSUMER	0%	0%	0%
MANUFACTURED	ITALY	ITALY	ITALY

ht ©2016 Happy Floors, Inc.
Miami, Florida