












Utah Specs

	TECHNICAL CHARACTERISTICS	REFERENCE STANDARD	REQUIRED VALUE	AVG. VALUE	
	DIMENSIONS	ISO 10545-2	Compliant	Compliant	
	WATER ABSORPTION	ISO 10545-3	≤0,5 %	<0,1%	
	MODULUS OF RUPTURE	ISO 10545-4	MODULUS OF RUPTURE R ≥ 35 N/mm ² BREAKING STRENGTH S ≥ 1300 N	R>50 N/mm ² S>2500 N	
	SCRATCH RESISTANCE	ISO 10545-7	0 - V	IV	
	LINEAR THERMAL EXPANSION	ISO 10545-8	≤ 9x10 ⁻⁵ °C ⁻¹	6x10 ⁻⁵ °C ⁻¹	
	THERMAL SHOCK RESISTANCE	ISO 10545-9	Resistant	Resistant	
	FROST RESISTANCE	ISO 10545-12	Resistant	Resistant	
	ACID AND ALKALI RESISTANCE	ISO 10545-13	CLASS GB MIN.	Low concentr. GLA High concentr. GHA	
	CHEMICAL RESISTANCE	ISO 10545-13	CLASS GB MIN.	GA	
	STAIN RESISTANCE	ISO 10545-14	CLASS 3 MIN.	5	
	FRICTION COEFFICIENT (SLIPPERINESS)	BCR - Italia DM del 14-06-89	ASTM - USA ASTM C1028	DIN - Germania DIN 51130	
		Dry rubber 0,62	Wet rubber 0,51	Dry leather 0,62	Dry neolythe 0,69
	DYNAMIC COEFFICIENT OF FRICTION (DCOF)	ANSI A137.1-2012	MIN. 0,42	> 0,74 Wet > 0,71 Dry	

THE PRODUCTS HAVING AN ABSORPTION < 0,5% ARE CLASSIFIED ACCORDING TO THE UNI CEN STANDARDS "FULLY VITRIFIED TILES" AND ACCORDING TO THE ASTM STANDARDS "IMPERVIOUS TILES"

**1/2 BROKEN JOINT NOT RECOMMENDED.
MANUFACTURE RECOMMENDS 1/3 OR LESS STAGGERED SPACING**



IMPORTANT
Please note that fixing in a 50% staggered configuration is not recommended. We suggest the following fixing configurations for these ceramic materials:

YES 15%



NO 50%

