



	Technical Specifications	Standard Requirements	Test Results	
			NATURAL	POLISHED
	Water Absorption UNI EN ISO 10545-03	<0.5%	E<0,1%	
	Breaking Strength UNI EN ISO 10545-04	Minimum: 1300 N	1800-2400 N	
	Modulus of Rupture UNI EN ISO 10545-04	Minimum: 35 N/mm ²	35-45 N/mm ²	
	Shock Resistance UNI EN ISO 10545-05	Suggested Minimum: e > 0,55	e 50,55 Restitution Coefficient	
	Resistance to Deep Abrasion UNI EN ISO 10545-06	Maximum: 175 mm ³	110-130 mm ³	
	Thermal Linear Expansion UNI EN ISO 10545-08 n	Minimum for Floor Applications: Class 3	27x10 ⁻⁶ °C	
	Thermal Shock Resistance UNI EN ISO 10545-09	Resistant	Resistant	
	Moisture Expansion UNI EN ISO 10545-10	As Reported	0,0%	
	Frost Resistance UNI EN ISO 10545-12	As Reported	Resistant	
	Chemical Resistance UNI EN ISO 10545-13	Domestic Chemical Products: UB/GB Acids And Alkalis: As Reported	UA ULC-UMC	
	Stain Resistance UNI EN ISO 10545-03	Minimum: Class 3	5	
	PEI Rating (Scratch Resistance) ASTM C 1027	As Reported	PEI IV	-
	Static Coefficient of Friction (COF) ASTM C 1028	For Level Interior Spaces Expected to be Walked Upon When wet: > 0.60	> 0.60	-
	Dynamic Coefficient of Friction (DCOF) ANSI A137.1	For Level Interior Spaces Expected to be Walked Upon When wet: > 0.42	> 0.42	-
	Thickness	As Reported	12" x 24" - 9 mm / 24" x 24" - 10 mm	
	Number of Screens	As Reported	12" x 24" - 24 / 24" x 24" - 12	



ALASKA

RECTIFIED PORCELAIN




1/2 BROKEN JOINT NOT RECOMMENDED






ALASKA

Rectified Porcelain



30" x 30" Glossy
30" x 30" Matte




24" x 24" Glossy
24" x 24" Matte




12" x 24" Glossy
12" x 24" Matte




6" x 24" Glossy
6" x 24" Matte



3" x 24" Bullnose Glossy
3" x 24" Bullnose Matte



2" x 2" Mosaic Glossy
12" x 12" Sheet
2" x 2" Mosaic Matte
12" x 12" Sheet



Hexagon Mosaic Glossy
10" x 14" Sheet
Hexagon Mosaic Matte
10" x 14" Sheet
Net Coverage: 0.80 sqft