














FRENCH QUARTER

	Technical Specifications	Reference Standard	Standard Requirements	Test Results	
	Water Absorption	UNI EN ISO 10545-03	<0.5%	< 0.2%	
	Breaking Strength	UNI EN ISO 10545-04	Minimum: 1300 N	≥ 1400 N	
	Modulus of Rupture	UNI EN ISO 10545-04	Minimum: 35 N/mm ²	≥ 37 N/mm ²	
	Shock Resistance	UNI EN ISO 10545-05	Suggested Minimum: e > 0.55	Complies	
	Resistance to Deep Abrasion	UNI EN ISO 10545-06	Maximum: 175 mm ³	Not Applicable	
	Thermal Linear Expansion	UNI EN ISO 10545-08	Minimum for Floor Applications: Classe 3	Complies	
	Thermal Shock Resistance	UNI EN ISO 10545-09	Resistant	Resistant	
	Moisture Expansion	UNI EN ISO 10545-10	As Reported	< 0.06%	
	Frost Resistance	UNI EN ISO 10545-12	As Reported	Resistant	
	Chemical Resistance	UNI EN ISO 10545-13	Domestic Chemical Products: UB / GB	GA	
			Acids and Alkalis: As Reported	GLA	
	Stain Resistance	UNI EN ISO 10545-14	Minimum: Classe 3	Class 5	
PEI	PEI Rating (Scratch Resistance)	ASTM C 1027	As Reported	Orleans	IV
				Chartres	V
				Bienville	IV
				Toulouse	IV
DCOF	Dynamic Coefficient of Friction (DCOF)	ANSI A137.1	For level Interior Spaces Expected to be Walked Upon When Wet : > 0.42	> 0.44	
V4	Shade Variation	Not Available	As Reported	V4	
	Thickness	Not Available	As Reported	8 mm	
	Number of Screens	Not Available	As Reported	24 (12"×24")	