











SILVER

	Technical Specifications	Reference Standard	Standard Requirements	Test Results
	Water Absorption	UNI EN ISO 10545-03	< 0.5 %	Meets requirements
	Breaking Strength	UNI EN ISO 10545-04	Minimum: 1300 N	>1300 N
	Modulus of Rupture	UNI EN ISO 10545-04	Minimum: 35 N/mm ²	> 35 N/mm ²
	Shock Resistance	UNI EN ISO 10545-05	Suggested Minimum: $\epsilon > 0.55$	> 0.55
	Resistance to Deep Abrasion	UNI EN ISO 10545-06	Maximum: 175 mm ³	175 mm ³
	Thermal Shock Resistance	UNI EN ISO 10545-09	Resistant	Meets requirements
	Frost Resistance	UNI EN ISO 10545-12	As Reported	Meets requirements
	Chemical Resistance	UNI EN ISO 10545-13	Domestic Chemical Products: GB / GB	GLA / GHA, GA
			Acids and Alkalis: As Reported	
	Stain Resistance	UNI EN ISO 10545-14	Minimum: Class 3	Class 3
PEI	PEI Rating (Scratch Resistance)	ASTM C 1027	As Reported	IV
DCOF	Dynamic Coefficient of Friction (DCOF)	ANSI A137.1	Per Lever Tester Spaces Expected to be Walked Upon When Wet ($\mu > 0.42$)	>0.42
V.2	Shade Variation	Not Available	As Reported	V.2
	Thickness	Not Available	As Reported	9mm
	Number of Screens	Not Available	As Reported	60